

Abstract of th Disclosure

An improved catalyst for producing carbon fibrils is made by incorporating an effective yield-enhancing amount of a carboxylate into a fibril-forming catalyst. Alternatively, such a catalyst is made by coprecipitating a compound of a metal having fibril-forming catalytic properties and an aluminum and/or magnesium compound, optionally in the presence of carbon particles or carbon fibril aggregates. The catalyst may also be made by incorporating a compound of a fibril-forming metal onto magnesia particles in carbon particles or carbon fibril aggregates. The catalysts, methods of using them to form carbon fibrils and those carbon fibrils are also disclosed.

BEST AVAILABLE COPY